

PAT-NO: JP02000154336A
DOCUMENT-IDENTIFIER: JP 2000154336 A
TITLE: PRIMER COMPOSITION AND BONDING OR COATING METHOD
PUBN-DATE: June 6, 2000

INVENTOR-INFORMATION:

NAME	COUNTRY
TAGUCHI, KOICHI	N/A
SUDO, HIROSHI	N/A

ASSIGNEE-INFORMATION:

NAME	COUNTRY
DENKI KAGAKU KOGYO KK	N/A

APPL-NO: JP10330696
APPL-DATE: November 20, 1998

INT-CL (IPC): C09D005/00 , C08J007/04 , C09D004/02 , C09J005/02

ABSTRACT:

PROBLEM TO BE SOLVED: To obtain a primer composition capable of improving adhesiveness and adhesion when bonding or coating a metal with a radically polymerizable curing resin by making the composition include a specific phosphoric ester (salt) and an acrylic monomer.

SOLUTION: This composition is obtained by including (A) an acid phosphoric ester (salt) represented by the formula $[R \text{ is } CH_2=CR_1CO(OR_2)_m \text{ [} R_1 \text{ is H or } CH_3; R_2 \text{ is } C_2H_4, C_3H_6, C_4H_8 \text{ or the like; (m) is 1-10]; (n) \text{ is 1 or 2}]$ (e.g. acid phosphooxyethyl methacrylate) in an amount of preferably 0.1-30 pts.wt., more preferably 0.5-10 pts.wt. based on 100 pts.wt. of the sum total of the components A and B and (B) an acrylic monomer [e.g. methyl (meth)acrylate] in an amount of preferably 70-99.9 pts.wt., more preferably 90-99.5 pts.wt. based on 100 pts.wt. of the sum total of the components A and B preferably without including a volatile solvent or water.

COPYRIGHT: (C)2000,JPO